



FABRIC TYPES

Cotton



MESH

32-43T (80-110) Mesh



SQUEEGEE

Medium 65° Shore Rectangular



STENCIL

Water resistant emulsion



CURE TEMPERATURE

3 minutes at 150°C (300°F)



PIGMENT LOADING

Up to 6% MagnaPrint® Eco Pigments



ADDITIVES

Crosslinker 100



STORAGE

In cool place properly closed:
> 5°C (40°F) < 25°C (77°F)



HEALTH & SAFETY

MSDS available upon request



CLEAN UP

Wash off screen using water
and mild detergent

MagnaPrint® Resist Paste

Ready to use print paste for wax batik effect

MagnaPrint® Resist Paste has been developed to simulate a wax Batik style of printing where a print is over dyed allowing the printed area to resist any of the colours from the dye bath.

It is designed to work best on cellulosic fibres which are subsequently dyed with direct or reactive dyestuffs.

Application

The fabric should be printed with the MagnaPrint® Resist Paste followed by drying and baked at 150°C (300°F) for 3 minutes.

If the style or design requires MagnaPrint® Resist Paste can be applied to the fabric by screen, paintbrush or even sprayed on to give the desired effect.

Please Note: Unless the fibre or yarn is totally covered with the print paste, dyestuff will fix to uncoated areas which will reduce the resist effect.

All information is given in good faith but without warranty. They do not release you from testing our products as to their suitability for the intended processes and uses.

MagnaColours® Ltd.

Dodworth Business Park, Upper Cliffe Road,
Dodworth, Barnsley, South Yorkshire,
S75 3SP, United Kingdom

www.magnacolours.com

tel: +44 (0) 1226 731751
fax: +44 (0) 1226 731752
email: info@magnacolours.com

Company registered in England No. 01378495, VAT No. GB 997 3172 70

