

Epic™ Top Score Standard Colors

Wilflex™ Epic Top Score Colors is a series of premixed athletic colors designed to meet the changing demands in the athletic market by delivering a solution for printing on polyester substrates that require low cure temperature.

Compliance

- ▶ Non-phthalate
- ▶ Compliant with CPSIA 2008 (Consumer Product Safety Improvement Act) Section 101, Lead Content in Substrates (<100 ppm lead); 16 CFR, Part 1303, Lead in Paint (<90 ppm lead); and CPSIA 2008, Section 108, Phthalates (<.1% DEHP, DBP, BBP, DINP, DIDP, DNOP)
- ▶ Epic Series - Eco-Passport Certified (Oeko-Tex)

Highlights

- ▶ Low cure properties.
- ▶ Delivers high stretch and bleed resistance in one package.
- ▶ Premix offering of most popular athletic colors.
- ▶ Accurate color reproduction on both print-flash-print and underbase print techniques.
- ▶ Matte finish.
- ▶ Low tack surface.
- ▶ Excellent printability.
- ▶ Convenient packaging.

Epic Top Score Standard Colors:

- ▶ 14600LBFF Epic Top Score Dark Gray
- ▶ 15350LBFF Epic Top Score Silver Gray
- ▶ 19000LBFF Epic Top Score Black
- ▶ 20100LBFF Epic Top Score Dark Brown
- ▶ 30150LBFF Epic Top Score Light Orange
- ▶ 30200LBFF Epic Top Score Bright Orange
- ▶ 30600LBFF Epic Top Score Texas Orange
- ▶ 30850LBFF Epic Top Score Burnt Orange
- ▶ 41850LBFF Epic Top Score Crimson
- ▶ 43000LBFF Epic Top Score National Red
- ▶ 44500LBFF Epic Top Score Light Maroon
- ▶ 57150LBFF Epic Top Score Purple
- ▶ 60500LBFF Epic Top Score Columbia Blue
- ▶ 62100LBFF Epic Top Score Royal Blue
- ▶ 66500LBFF Epic Top Score Navy
- ▶ 67850LBFF Epic Top Score Aqua
- ▶ 70000LBFF Epic Top Score Kelly Green
- ▶ 70200LBFF Epic Top Score Dark Green
- ▶ 80500LBFF Epic Top Score Old Gold
- ▶ 80000LBFF Epic Top Score Gold
- ▶ 86780LBFF Epic Top Score Vegas Gold

Printing Tips

- ▶ For optimal bleed resistance, print Epic PolyWhite, the most bleed resistant white in the Wilflex line, as underbase. Set the dryer belt at the highest possible speed while still ensuring that the ink film reaches 300°F (149°C). For optimal stretch, print Epic Performance White as underbase. Set the dryer belt at the highest possible speed while still ensuring that the ink film reaches 290°F (143°C).
 - ▶ Building a thick ink deposit on the polyester substrate provides additional bleed blocking power. To accomplish this, use the following coating screen method, wet-on-wet application:
 - ▶ 1st Coat - Print side
 - ▶ 2nd Coat - Squeegee side
 - ▶ 3rd Coat - Print side
 - ▶ 4th Coat - Squeegee side
- Always end your coating on the squeegee side to push the emulsion to the print side. Dry screens print side facing the floor. Optimal emulsion over mesh is 25% or higher.
- ▶ If printing on a hard metal surface, use a palette covering to allow for a softer printing surface.
 - ▶ Polyester fabrics are likely to have dye migration issues and may require use of additional bleed blocker, such as Epic Performance Underbase Gray. To determine a material's bleed potential, please reference the testing procedures outlined in the Wilflex User's Manual.


continued on page 2

Printing Parameters

Opacity	9	
Bleed Resistance	8	
Smooth Surface	9	
Flash	7	
Gloss	2	
Printability	8	




Fabric Types
100% polyester, polyester blends, 100% nylon jersey



Mesh
Counts: 86-160 t/in (34-90 t/cm)
Tension: 25 n/cm²



Squeegee
Durometer: 60-70
Edge: Square, Sharp
Stroke: Hard flood, slow to medium speed
*Avoid excess pressure.



Non-Phthalate Stencil
Direct: 2 over 2
Capillary/thick film: 30+ micron
Off contact: 1/16" (.2 cm)



Gel/Cure Temperature
Gel: 220°F (104°C)
Cure: 290°F (143°C)



Epic Pigment Loading
N/A



Additives
Extender: N/A
Reducer: Viscosity Buster - 1% max



Storage
65°-90°F (18°-32°C)
Avoid direct sun.
Use within one year of receipt.



Clean Up
Ink degradable or press wash



Health & Safety
MSDS: www.polyone.com

www.wilflex.com/pib

PolyOne Wilflex™ inks by PolyOne.

©2013 PolyOne Corporation All Rights Reserved. Effective 3/04/2013. Not all Wilflex products are available in every country. The information in this publication is based on information and experience believed reliable. Since many factors may affect processing for an application, processors must carry out their own tests and experiments to confirm suitability for intended use. You must make your own determination of suitability for your intended use and environmental acceptability, the safety and health of your employees, and purchasers of your product.

World Headquarters
8501 Hedge Lane Terrace, Shawnee, KS 66227-3290
E-mail: CServ@SourceOneOnline.com - www.SourceOneOnline.com

Northeast: 1-800-257-8226
Southeast: 1-800-537-4606
Midwest: 1-800-736-7636

West: 1-800-252-7767
Mexico: 52 (55) 4777-1900
Honduras: 504-574-9390

©2013 Nazdar. All Rights Reserved. SourceOne and CATZper are registered trademarks of Nazdar. All other trademarks are the property of their respective owners. Specifications subject to change without notice.

Precautions

- ▶ Perform fusion tests before production. Failure to cure ink properly may result in poor wash fastness, inferior adhesion and unacceptable durability. Ink gel and cure temperatures should be measured using a Thermoprobe placed directly in the wet ink film and verified on the production run substrate(s) and production equipment. It is the responsibility of the printer to determine that the correct ink has been selected for a specific substrate and the application processes meet your customer's standards or specifications.
- ▶ Pretest Epic Top Score inks on garments that could be susceptible to ghosting. Avoid stacking printed garments hot as some fabric dyes are prone to color distortion. Fabric and dye characteristics can vary between manufacturers and from dye lot to dye lot.
- ▶ Use of Equalizers are not recommended and may affect the bleed and stretch properties of the ink.
- ▶ Avoid overflashing, as it can result in poor inter-coat adhesion of overprint colors.
- ▶ Stir inks before printing.
- ▶ Do not dry clean, bleach or iron printed area.
- ▶ NON-CONTAMINATION OF EPIC INKS : Do not add or mix non-Epic inks, additives or extenders with the Epic ink products. All buckets, palette knives, stirring apparatus, squeegees, flood bars and screens must be cleaned properly and free of phthalate containing inks. Non-phthalate emulsions and pallet adhesives must be used.
- ▶ Any application not referred in this product bulletin should be pre-tested or consultation sought with Technical Services Department prior to printing.
- ▶ Email: techserviceswilflex@polyone.com



©2013 PolyOne Corporation All Rights Reserved. Effective 3/04/2013. Not all Wilflex products are available in every country. The information in this publication is based on information and experience believed reliable. Since many factors may affect processing for an application, processors must carry out their own tests and experiments to confirm suitability for intended use. You must make your own determination of suitability for your intended use and environmental acceptability, the safety and health of your employees, and purchasers of your product.



World Headquarters
8501 Hedge Lane Terrace, Shawnee, KS 66227-3290
E-mail: CServ@SourceOneOnline.com - www.SourceOneOnline.com

Northeast: 1-800-257-8226
Southeast: 1-800-537-4606
Midwest: 1-800-736-7636

West: 1-800-252-7767
Mexico: 52 (55) 4777-1900
Honduras: 504-574-9390

©2013 Nazdar. All Rights Reserved. SourceOne and CATZper are registered trademarks of Nazdar. All other trademarks are the property of their respective owners. Specifications subject to change without notice.